

INTRODUCTION

DESCRIPTION

Wax paste based on beeswax, carnauba wax, candelilla wax, turpentine essence, silicone-free.

USES

For inside use.

Protection of mineral, concrete and timber, etc. cladding

ADVANTAGES

- Feeds
- Regenerates
- Protects
- Makes the substrate shine

TECHNICAL SPECIFICATION

IDENTIFICATION DATA	
State	Solid
Appearance	Paste
Colour	Off-white
Odour	Characteristic
Density NBN EN 1015-10	814 kg/m ³
Apparent density (at 20°C)	0.814 kg/L
Packaging	350 ml pots 2.5L pots
Storage	6 months in a dry spot, sheltered from frost, in the original unopened packaging.
Volatile Organic Component content	73,71 %
Customs classification	34 04 90 10
ADR classification	"A 1993 FLAMMABLE LIQUID, 3, III, (D/E)"
APPLICATION DATA	
Consumption	20 to 60 g/m ² according to porosity
Application temperature	+10°C min to +30°C max
Drying time (at 20°C)	30 minutes

APPLICATION

SUBSTRATE AND PREPARATION

The substrate must be sound, dry before and after application, clean, matt, free from dust and non-oily. It must be hard, not vulnerable to frost and not floury.

PREPARATION OF THE MIXTURE

BEALWAX is applied straight from the tin.

USE

Apply with a paintbrush or cloth (white cotton to avoid any colouring of the wax by the pigments contained in coloured fabrics).

Leave to dry for 30 minutes.

Consult the legal notice at the end of the document

Page n°1 - This technical sheet comprises 2 page(s) - Edition NF 1/09/15 - This version supersedes all previous versions.

POLISHING

After it has dried thoroughly, polish it with a "sheepskin" disk, which will give it a satin finish, while continuing to spread the product into the surface.

MISCELLANEOUS

CLEANING TOOLS

Clean the product off dry while still fresh or with turpentine, using a spatula or a cloth.

MAINTENANCE

Surfaces treated with **BEALWAX** need to be maintained without a mordant agent.

For keeping clean: **FINISH SA TR** diluted in water.

To eliminate limescale (plumbing fittings also): vinegar diluted in water. Start with low concentrations and increase according to the hardness of the water.

To renew the protection: application with a cloth of a new pass of **BEALWAX** 1 to 2 times a year at least and before losing the "beading" effect, taking care to remove any limescale residue beforehand.

WARNINGS

Sites must be protected against rain, sun, wind and frost until drying is complete.

It is extremely inadvisable to apply media containing salts (sodium sulphate, nitrates, calcium, etc.).

ADVICE

Follow the application instructions exactly, according to the purpose of the product. Never use products other than those shown in this technical data sheet, to avoid any risk of things going wrong.

Always carry out tests with the chosen protection, as each pigment and each protection reacts differently.

For a single site and for each product type, always use products bearing the same batch number.

ENVIRONMENT

Remove waste to a specialist collection centre.

SAFETY

Inflammable product. Causes respiratory problems if ingested. Keep out of reach of children. If ingested, consult a specialist. Consult the safety data sheet available on request or at www.beal.be

LEGAL NOTICE

These instructions, and , in particular, the recommendations for the application and final use of the products, are provided in good faith and are based on the knowledge and experience that the BEAL Corporation has acquired to date about its products when they have been properly stored, handled and applied under normal conditions. In practice, the differences between materials, substrates and specific conditions on site are such that this information or any written recommendation or advice given do not imply any guarantee of merchantable quality other than the statutory guarantee against hidden defects. Our liability cannot be committed in any way, assuming an application not compliant with our teaching. None of the data and information relating to suitability and application absolve the client from the need to carry out its own verifications and tests. All orders are accepted subject to our current terms and conditions of trading. It is essential that users consult the most recent version of the instructions for the product in question. These will be delivered to them on request.

Consult the legal notice at the end of the document

Page n°2 - This technical sheet comprises 2 page(s) - Edition NF 1/09/15 - This version supersedes all previous versions.